

Material Description

SERIFILL 15K25TN808 is a talc filled Polypropylene Copolymer Compound, obtained from industrial scraps and prime materials. This product has a fluidity suitable for injection molding, color black 808 (FIAT norm) and good thermo-mechanical properties . It is currently used in items where good dimensional firmness is required. It is specially used for automotive applications, where high processability and a good appearance are expected.

Material Properties and Test Requirements

TYPICAL PHYSICAL VALUES

Proprietà fisiche	U. M.	Valore	Metodo
Melt Flow Index (230°C - 2,16 kg)	g/10'	15 *	ISO 1133
Density (23°C)	g/cm ³	1.05÷1.10	ISO 1183
Ash content (525°C-45')	%	22÷27	ISO 3451
Moisture (loss in weight)	%	0.05	ASTM D6980
* if not otherwise agreed with client			
Proprietà meccaniche			
Flexural Modulus (2mm/min)	MPa	≥2200	ISO 178
Izod notched impact strenght (23°C)	Kj/m ²	4	ISO 180
Proprietà termiche			
Vicat 50N	°C	≥64	ISO 306

Working condition

Melting Temperature: 190 - 220 °C
 Mould Temperature: 40 - 50 °C
 Injection speed: medium-high
 Minimum time of Drying: about 3 hours at 100°C

Packaging and storage

Granules are packaged in big bags of 1200 kg or can be shipped in bulk.
 Material must be stored in dry rooms, at ambient temperature and protected from the direct sunlight.

The dates referred above are indicatives and have not to be considered as product specifications. Because the condition in which our information and our product will be used are not predictable, our society do not guarantee the applicability and fitness of product for the use that will be done; so we decline for any responsibility for damage at the client or third parties.

Revision	Date	Written by	QA Approval
D	24/07/14	Serena D'Addio	Giuseppe Magliulo
This document has been electronically written and printed. Due to this reason signatures aren't included.			