

## Material Description

Il SERIFILL KT20N808 is a talc filled Polypropylene Copolymer Compound, obtained from industrial scraps and prime materials. This product has a fluidity suitable for injection molding, colour black 808 (FIAT norm) and good thermo-mechanical properties. It is currently used in items where good dimensional firmness is required. It is specially used for automotive applications, where high processability and a good appearance are expected.

## Material Properties and Test Requirements

### TYPICAL PHYSICAL VALUES

Proprietà fisiche	U. M.	Valore	Metodo
Melt Flow Index (230°C - 2,16 kg)	g/10'	10÷15	ISO 1133
Density (23°C)	g/cm <sup>3</sup>	1.01÷1.05	ISO 1183
Ash content (525°C-45')	%	17÷21	ISO 3451
Moisture (loss in weight)	%	0.05	ASTM D6980
Proprietà meccaniche			
Flexural Modulus (2mm/min)	MPa	2000	ISO 178
Izod notched impact strenght (23°C)	Kj/m <sup>2</sup>	≥5	ISO 180
Proprietà termiche			
Vicat 50N	°C	≥64	ISO 306

## Working condition

Melting Temperature: 190 - 220 °C  
 Mould Temperature: 40 - 50 °C  
 Injection speed: medium-high  
 Minimum time of Drying : about 3 hours at 100 °C

## Packaging and storage

Granules are packaged in big bags of 1200 kg or can be shipped in bulk.  
 Material must be stored in dry rooms, at ambient temperature and protected from the direct sunlight.

The dates referred above are indicatives and have not to be considered as product specifications. Because the condition in which our information and our product will be used are not predictable, our society do not guarantee the applicability and fitness of product for the use that will be done; so we decline for any responsibility for damage at the client or third parties.

Revision	Date	Written by	QA Approval
B	25/07/14	Serena D'Addio	Giuseppe Magliulo

This document has been electronically written and printed. Due to this reason signatures aren't included.



C.N. 9190 SRRE

### SERI PLAST Srl Office

Strada Prov.le per Gioia snc - Centro Aziendale Quercete  
 81016 SAN POTITO SANNITICO (CE)  
 Tel: +39 0823 786235 - Fax: +39 0823 543828  
 info@serihg.com - www.serihg.com

### Production

Strada Provinciale 246 Torrione - Puglianello  
 Loc. Contrada Vernelle  
 81011 ALIFE (CE)  
 Tel: +39 0823 785720 - Fax: +39 0823 543828

Iscr. Reg. Imp. Caserta  
 P. IVA IT 03591990613  
 Cap. Soc. € 1.945.000,00 i. v.